













士峰科技股份有限公司

SHIFENG TECHNOLOGY CO., LTD.

Product No.	Structure	Appearance	Melting Point	Clearing Point
RMS002		White Powder	58	122
RMS003		White Powder	103	
RMS006		White Powder	96	
RMS008		White Powder	68	73
RMS009		White Powder	81-84	
RMS015		White Powder	38	
RMS020		White Powder	62	
RMS021		White Powder	48	54
RMS022		White Powder	97	
RMS024		White Powder	52 93 108	113
RMS025		White Powder	53 60 104	126
RMS026		White Powder	73 133	146
RMS027		White Powder	121	

地址:709台南市安南區工業二路31號 研二館411室

電話: (06)384-1250











<http://www.sf-tec.com>

傳真: (06)384-1260

E-mail:sales@sf-tec.com

士峰科技股份有限公司

SHIFENG TECHNOLOGY CO., LTD.

Product No.	Structure	Appearance	Melting Point	Clearing Point
RMS028		White Powder	97	118
RMS042		White Powder	41	139
RMS043		White Powder	36	110
RMS044		White Powder	61	138
RMS045		White Powder	49	
RMS046		White Powder	53	
RMS047		White Powder	47	
RMS048		White Powder	83	180
RMS049		White Powder	86	188
RMS050		White Powder	65	

RM Single (code)	No (589)	Ne (589)	Δn (589)	Patent
RMS002	1.4993	1.6463	0.147	Unfree
RMS008	1.5114	1.6768	0.1654	Free
RMS009	1.5004	1.6193	0.1189	Free
RMS020	1.5079	1.6528	0.1449	Free
RMS021	1.5174	1.6378	0.1204	Free

地址:709台南市安南區工業二路31號 研二館411室

電話: (06)384-1250

<http://www.sf-tec.com>

傳真: (06)384-1260

E-mail:sales@sf-tec.com